

**MATERIAL FIRE CLASSIFICATION
REPORT**

pursuant to article 5 of the decree of 21 November 2002

VALID FOR 5 YEARS from 12 May 2014**NO. P125483 -****DE/5**

and appendix of 3 pages

Material submitted by: FILMOLUX SARL
300 rue Etienne Marcel
93170 BAGNOLET**Trademark:** FILMOLUX PHOTO SATIN**Brief description:****Overall composition:** Material consisting of flexible, transparent, satinised PVC film and polyacrylate water-based adhesive à base applied at 35g/m²**Application :** Protective film**Weight:** (117 ± 5) g/m²**Thickness:** (0.148 ± 0,005) mm**Colour:** Structured transparent**Test reports:** No. P125483 - DE/5 of 12 May 2014**Nature of tests:** Radiation test NF P 92-501 (December 1995).**NF P 92-507 (February 2004)****Classification:** **M1** APPLIED TO STEEL PLATE 15/10th mm thick**VALID FOR ANY APPLICATION FOR A PRODUCT FOR WHICH EC MARKING IS NOT REQUIRED****Duration of classification (NF P 92-512 : 1986) : APPARENTLY UNLIMITED**

In view of the criteria resulting from the tests described in test report No. P125483 - DE/5 enclosed.

This report only states the characteristics of the sample subjected to testing and does not prejudice the characteristics of similar products. It does not constitute product certification within the meaning of article L. 115-27 of the Code of Consumption and the law of 3 June 1994.

Reproduction is permitted only in full of either this one-page Classification report or the entire Report and appendix consisting of 4 pages.

Trappes, 12 May 2014

Morristraduction
6 Santoline, Le Mas du Clos
84220 Roussillon, FranceManager of the Department of the
Performance in Fire and Fire
Safety Department

Sophie THIEFFRY

on www.cofrac.fr

National laboratory for metrology and testing

Public organisation of an industrial and commercial nature • Registered office: 1, rue Gaston Boissier - 75724 Paris Cedex 15 • Tel.: 01 40 43 37 00
Fax: 01 40 43 37 37 • E-mail: info@lne.fr • Internet: www.lne.fr • Siret (French business registration number): 313 320 244 00012 • NAF (French business activity code): 743 B • VAT: FR 92 313 320 244 Barclays Paris Centrale IBAN: FR76 3058 8600 0149 7267 4010 170 BIC: BARCFRPP



MATERIAL FIRE CLASSIFICATION REPORT

pursuant to article 5 of the decree of 21 November 2002

VALID FOR 5 YEARS from 12 May 2014

NO P125483 - DE/5

1. PURPOSE OF TESTING

The tests to which this test report refers are for the purpose of determining the fire-resistance classification of the material, in accordance with the requirements of the Order of the Ministry of the Interior dated 21 November 2002.

2. PROVENANCE AND CHARACTERISTICS OF THE SAMPLES

Application for testing from	: FILMOLUX SARL
Date and reference of order:	Good for approval under specification no. 2014/5901 dated 07/04/2014
Manufacturer	: NESCHEN AG HANS NESCHEN STRASSE 31675 BÜCKEBURG Germany
Trademark and reference:	FILMOLUX PHOTO SATIN
Overall composition:	Material consisting of flexible, transparent, satinised PVC film and water-based polyacrylate adhesive applied at 35g/m ²
Characteristics attested to by the applicant	:
Weight	: (117 ± 5) g/m ²
Thickness	: (0.148 ± 0.005) mm
Colour	: Structured transparent

Report continued on next page



Appendix
page 2**3. TESTING METHODS**Date of receipt of test-tubes: 11/04/2014Packaging of test-tubes prior to testing:

The test-tubes subsequently placed on their subjectiles were packaged before testing in an atmosphere of $(23 \pm 2)^{\circ}\text{C}$ and $(50 \pm 5)\%$ relative humidity for seven days or until a constant mass was obtained (in the case of materials that were delivered wet or that were very thick).

The mass was considered to be constant when two successive weighings at 24-hour intervals did not vary by more than 0.1% or by 0.1 g (the greatest weight was used).

Date of performance of tests: 07/05/2014**4. RESULTS****4.1. RADIATION TESTING**

	Test-tube 1	Test-tube 2	Test-tube 3	Test-tube 4	
Moment of first flaming exposed surface (ti1)	—	—	—	—	
Moment of first flaming non-exposed surface (ti2)	—	—	—	—	
Sum of flame heights H (cm)	0	0	0	0	
Sum of duration of effective combustion	0	0	0	0	average
$\varrho = \frac{100 \times \sum H}{n \sqrt{\sum \Delta T}}$	0	0	0	0	0
Fall of non-flaming drops	No	No	No	No	
Fall of flaming drops	No	No	No	No	

report continued on next page



AV

Page 3
appendix

5. **OBSERVATIONS ABOUT THE TESTS**

NONE.

6. **CONCLUSION AND CLASSIFICATION**

As a result of the tests, the material submitted having the characteristics described on the first page of this test report obtained the classification:

M1 ADHERED TO STEEL PLATE OF A THICKNESS OF 15/10th mm

VALID FOR ANY APPLICATION FOR A PRODUCT THAT DOES NOT REQUIRE EC MARKING

To determine the classification, no account was taken of the uncertainty associated with the result.

7. **DURATION OF THE CLASSIFICATION**

APPARENTLY UNLIMITED

Trappes, 12 May 2014



Manager of the Department of the
Performance in Fire and Fire
Safety Department

Sophie THIEFFRY

The results stated are only applicable to samples, products or materials submitted to LNE and as they are defined in the present document.