

# PRODUCT DATA SHEET

## Avery Dennison<sup>®</sup> MPI 2006 HOP Hi-Tack

Issued: 04/2021

### Introduction

Avery Dennison Multi Purpose Inkjet 2006 HOP Hi-Tack is a gloss, white polymeric self-adhesive vinyl. Due to its special adhesive it is suitable for difficult to adhere to surfaces such as low surface energy substrates (eg. HDPE or PP) and matt interior painted walls.

As all of the HOP series products, it allows to cover a full range of flat and slightly curved medium term regular and over posting applications.

Avery Dennison MPI 2006 HOP Hi-Tack is highly recommended for a wide range of applications on flat and slightly curved substrates.

### Conversion

MPI 2006 HOP Hi-Tack is a multi-purpose vinyl, developed for use on various super wide format printers using hard solvent, eco/mild solvent, UV-curing or latex inks.

To enhance colour and to protect images against UV radiation and abrasion, it is recommended to protect Avery Dennison MPI 2006 HOP Hi-Tack using an overlamine or varnish.

For recommended combinations of DOL films and media, please refer to “Technical Bulletin 5.3. Recommended combinations of Avery Dennison<sup>®</sup> Overlaminates and Avery Dennison<sup>®</sup> Digital Print Media”.

### Recommendations

Avery Dennison MPI 2006 HOP Hi-Tack is recommended for a variety of applications to flat or slightly curved low-energy surfaces, such as:

- » Vehicle graphics
- » Architectural interior & exterior signs
- » Promotional and point of sale advertising
- » Exhibitions

### Features

- » Excellent printability and handling on selected printers.
- » Outstanding adhesion to low energy surfaces, a solution for PP and PE substrates.
- » Prolonged outdoor durability of up to 7 years unprinted.
- » High gloss, matt or lustre finishes\*.

\* when used in combination with DOL 2460 Gloss, DOL 2470 Matt or DOL 2480 Lustre overlaminates.



#### Face Film

80 micron gloss white polymeric calendered vinyl with high opacity properties.



#### Adhesive

Permanent, acrylic based; designed for low-surface energy substrates.



#### Backing

StaFlat liner, 145 g/m2.



#### Durability

7 years



#### Shelf Life

2 years

## Physical Characteristics

Features	Test method <sup>1</sup>	Results
Caliper, facefilm	ISO 534	80 micron
Caliper, facefilm + adhesive	ISO 534	120 micron
Dimensional stability	FINAT FTM 14	1.0 mm max.
Adhesion, initial	FINAT FTM-1, HDPE	520 N/m
Adhesion, ultimate	FINAT FTM-1, HDPE	600 N/m
Flammability		Self-extinguishing
Shelf life	Stored at 230C/50-55% RH	2 years
Durability <sup>2</sup>	Vertical exposure	7 years

### Temperature range

Features	Results
Application temperature:	≥ 10 °C
Service temperature:	-40°C to +80°

NOTE: Materials have to be properly dried before further processing, for example laminating, varnishing or application. The residual solvents could change the products' specific features.

For good print and converting result we recommend to let the rolls acclimatize in the print/lamination room at least 24h. before printing or converting. Too much temperature or humidity deviation between material and room climate can cause layflatness and/or printability issues.

Generally, constant material storage conditions of ideally 20°C (+/-2°C) /50% RH (+/- 5%), without too big climate deviations, will support a more robust and stable printing/converting process. For further details, please refer to TB 1.11.

## Important

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

1) Test methods: More information about our test methods can be found on our website.

*Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>.*

*Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.*

*© 2021 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.*